4870–4875

Sn60/Pb40 No-Clean Solder Wires

4870–4875 electronic grade solder wires use a tin-to-lead alloy ratio, with a no-clean, synthetically refined, splatter-proof resin flux core. They melt at a higher and wider temperature range than 63/37 solder. They create robust and reliable joints that are highly resistant to whisker formation.

These leaded solders achieve a consistent solder and flux percentage thanks to our state-ofthe-art extrusion wire-drawing machine, which continuously monitors the wire to prevent voids and ensure consistency, providing a top-grade solder wire.

Features & Benefits

- Alloy exceeds J-STD-006C and meets ASTM B 32 purity requirements
- Flux meets J-STD-004B for ROM1
- Particle size Type 3
- Excellent 12 mil fine pitch printing capability
- Long operational life—non-slumping
- · Good wettability
- Halogen-free

Available Packaging

Cat. No.	Packaging	Gauge	Diameter	Net Wt.
4870-18G	Pocket pack	21	0.032"	18 g
4875-227G	Spool	21	0.032"	227 g

Contact Information

MG Chemicals, 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com

Phone: North America: +(1)800-340-0772 International: +(1) 905-331-1396 Europe: +(44)1663 362888





Properties

Flux Classification	REL0	
Flux Type	Resin	
Flux Activity	Low	
Copper Mirror	No removal	
Corrosion Test	Pass	
Electromigration	Pass	
Silver Chromate–Cl- + Br-	Pass	
Flux Residue Dryness	Pass	
Acid Number (mgKOH/g sample)	100	
Softening Point of Flux Extract	24	°C
Solder Spread	130	mm ²
Splitting of Flux-Cored Wire Solder	0.30	%
Halides (by weight)	<0.05	%
Post Reflow Flux Residue	45	%
Suface Insulation Resistance (SIR)	2.4 x 10 ¹⁰	Ω
Bellcore (Telecordia)	4.1 x 10 ¹⁰	Ω

Storage and Handling

Store refrigerated between 18–25 °C away from direct heat or sunlight.



This product can expose you to chemicals including lead, which is known to the State of California to cause cancer and birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.