

ISO 9001:2015 Registered Quality System. Burlington, Ontario, CANADA SAI Global File: 004008

824-Aerosol

Description

The 824 *Isopropyl Alcohol* (IPA) is a high purity cleaner and solvent. The purity level meets *Grade A* standard for *MIL Spec TT-I-735A* and *ASTM D770*, ensuring that no contamination occurs from its use.

As a cleaner, it is fully miscible in water and most organic fluids, making it good at dissolving dirt, light organic contaminants, and ionic flux residues. Since the 824 is highly anhydrous (without water) and hygroscopic (absorbs humidity), it readily scavenges water off surfaces, trapping the water in the IPA solution as an azeotropic mixture. This helps to dehumidify surfaces.

As a solvent, it acts as a moderate evaporation, 'plastic safe' diluent (see compatibility chart on page 3) and is used to improve the properties of paint resins and other heterogeneous solid mixtures. Therefore, it serves as a useful carrier solvent to adjust the rheological properties and compatibilities of complex mixtures. Due to IPA's volatility, it resists entrapment in the coating. As it dries, it gives off a very light odor, which is not bothersome but serves as a cue to limit over-exposure due to poor ventilation.

Applications & Usages

Since the 824 is safe for most plastics, seals, ceramics, and printed circuit board components, it is used heavily in the electronics industry. It is great for cleaning screens, stencils, fiber optics, cables, keypads, printed circuit board components, or electrical contacts and connectors. It is also used to clean oxides and grime on audio or video tape heads. It effectively removes light greases, oils, and flux without adding additional residues to contacts, relays, and circuit boards connectors. It is quick drying relative to water. Further, it can be used to wash off more aggressive organic solvents like acetone or toluene.

Features and Benefits

- Suitable for Use in Food Facilities as a Non-Food Chemical—Canadian and NFS recognition letters available on request
- Meets MIL Spec TT-I-735A and ASTM D770
- Meets reagent ACS and USP/NF Grades
- Anhydrous solvent—Removes water and humidity from components leaving them dry
- Less than 0.001 g/100 mL non-volatile residues
- Excellent "Green Solvent" scores
- Safe for aqueous environments
- Low toxicity

Storage Properties

Properties	Value
Shelf Life @22 °C [72 °F] Storage Temperature Limits a)	5 y -20 to 40 °C [-4 to 104 °F]

a) Store in cool, dry, and well ventilated area.

Page **1** of **5**



ISO 9001:2015 Registered Quality System. Burlington, Ontario, CANADA SAI Global File: 004008

824-Aerosol

Mil Spec #TT-I-735A

Physical Properties	Method	Grade A Specifications
Purity	Gas chromatography	>99.8%
Water (w/w)	ASTM D 1364	≤0.10%
Color (Pt-Co scale)	ASTM D 1209	≤5
Acidity (% of acetic acid)	ASTM D 1613	≤0.001
Density @20 °C [68 °F]	ASTM D 4052	0.785—0.786 g/mL
Specific gravity @20 °C / 20 °C	ASTM D 4052	0.785—0.787 g/mL
Dilution range	ASTM D 1078	-
Initial boiling point	"	≥81.8 °C
Dry point	"	≥82.8 °C
Nonvolatile matter	ASTM D 1353	≤0.001 g/100 mL
Water miscibility	ASTM D 1772	Clear and miscible
Appearance	ASTM D 4176	Clear, free from sediment, and
		suspended matter

Properties

Physical Properties	Method	Value
Odor	_	Mild alcohol
Color	Visual	Colorless
Refractive Index @20 °C [68 °F]	ASTM D 1218	1.3766
Evaporation Rate (ButAc =1)	Literature	2.9
Heat Capacity	"	11 400 kJ/m [0.612 BTU·in/h·ft2·°F]
Viscosity	n n	3.4 cP
Safety Properties	Method	Value
Flammability	Literature	Highly flammable liquid and vapor
Flash Point	"	12 °C [54 °F]
Boiling Point	"	82 °C [180 °F]
Auto-ignition	"	425 °C [797 °F]
Volatile Organic Content (VOC)	"	100%
Environmental Properties	Method	Value
Toxicity for Aqueous Environment	Literature	Very low toxicity
Biodegration	II .	Readily biodegradable



ISO 9001:2015 Registered Quality System. Burlington, Ontario, CANADA SAI Global File: 004008

824-Aerosol

Solvation Parameters	Value			
Solubility in water (%wt)	∞ Fully Miso	∞ Fully Miscible		
Solubility for water (%wt)	∞ Fully Miso	∞ Fully Miscible		
Dielectric constant @20 °C [68 °F]	17.5	17.5		
Surface Tension @25 °C [75 °F] (dynes/cm)	21.4			
Hansen Solubility Parameters	(MPa) ^{1/2}	[cal/cm³]½		
Total	23.5	[11.5]		
Non-Polar	15.8	[7.7]		
Polar	6.1	[3.0]		
Hydrogen Bonding	16.4	[8.0]		

Note: Typical literature values

Compatibility

It is compatible with many plastics, seals, PCB components, paints, rubbers, and plant fibers.

Substrate Compatibility: Consult the 824 compatibility chart for a tentative compatibility list. These compatibility ratings should be considered as tentative due to variations in plastic manufacturers' formulations and additives, as well as the processing conditions during cleaning.

<u>ATTENTION!</u> Always perform a compatibility test on a non-critical area or a representative test substrate prior to use. Test even if the compatibility chart predicts a high compatibility: modern parts may incorporate undeclared sensitive materials (such as custom plastic blends, custom additives, protective coatings, or decorative coatings).

824 Plastics Compatibility Chart

Plastic type	Resistance
Epoxy	Excellent
ABS (acrylonitrile butadiene styrene)	Fair to Poor
PMMA (acrylic and plexiglass)	Poor
PVC (polyvinyl chloride)	Excellent
HD-PE (high density polyethylene)	Excellent
LD-PE (low density polyethylene)	Excellent
PP (polypropylene)	Excellent
PS (polystyrene)	Excellent
PC (polycarbonate)	Excellent
Nylon	Poor to Severe

Note: Rating is given for room temperature only. Heating the solution generally decreases the chemical resistance.

LEGEND

Excellent = Negligible chemical attack over long exposures

Good = Slight attack with minor absorption over long exposures

Fair = Moderate attack with swelling,
 softening, loss of strength (may
 tolerate short term exposures)

Poor = Not recommended due to possible crazing, cracking, discoloration, or loss of strength

Severe Effect = Decomposition or dissolution after short exposures

ISO 9001:2015 Registered Quality System. Burlington, Ontario, CANADA SAI Global File: 004008

824-Aerosol

824 Elastomers Compatibility Chart

Plastic type	Resistance
Nitrile	Good
Neoprene	Good
Silicone	Excellent
Butyl Rubber	Excellent
Latex	Excellent
PVC (polyvinyl chloride)	Good
Polyvinyl Alcohol	Severe Effect
Viton	Excellent

Note: Rating is given for room temperature only. Heating the solution generally decreases the chemical resistance.

<u>ATTENTION!</u> Do NOT use on computer monitors, tablet screens, or eyeglasses. This solvent is too powerful for the coatings used on these devices.

Health, Safety, and Environmental Awareness

Please see the 824 **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

Application Instructions

Follow the procedure below for best results.

To clean residues

- Spray rinse area directly or use with a hog hair cleaning brush to loosen and remove contamination.
 - a. Ensure that wash runs off the circuit board along the shortest unencumbered path to prevent redeposit of solvated residues.

Packaging and Supporting Products

Cat. No.	Packaging	Net Volume	Net Volume		ht
824-450G	Aerosol	553 mL	18.7 fl oz	450 g	14.5 oz
824-450GCA	Aerosol	553 mL	18.7 fl oz	450 g	14.5 oz
824-400ML	Aerosol	400 mL	13.5 fl oz	325 g	11.4 oz

ISO 9001:2015 Registered Quality System. Burlington, Ontario, CANADA SAI Global File: 004008

824-Aerosol

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAOs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+(1) 905-331-1396 (International) +(44) 1663 362888 (UK & Europe)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: Manufacturing & Support Head Office

1210 Corporate Drive 9347–193rd Street

Burlington, Ontario, Canada Surrey, British Columbia, Canada

L7L 5R6 V4N 4E7

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.