

### Description

The 4900–4917 SAC305 No Clean Solder Wire is an electronic grade solder wire. It uses the predominant lead-free alloy composition and exceeds J-STD-006C and meets ASTM B 32 purity specifications. It is complemented with a no clean, synthetically refined, splatter-proof resin flux core that is classified as RELO according to J-STD-004B. This solder is a great alternative to leaded solders.

The 4900–4917 solders achieve a consistent solder and flux percentage through a state-of-the-art, extrusion, wire-drawing machine. This machine continually monitors the wire to prevent voids and ensure consistency, providing a top-grade solder wire.

### Benefits & Features

- **Lead free & no clean**
- **Alloy exceeds J-STD-006C and meets ASTM B 32 purity requirements**
- **Flux meets J-STD-004B**
- **The resin spreads like rosin-activated flux**
- **Virtually non-splattering**
- **Non-corrosive**
- **Non-conductive residue**
- **Halide free**
- **About 14% longer by weight than leaded solder wires**
- **Suitable for Use in Food Facilities as a Non-Food Chemical**—Canadian and NFS recognition letters available on request

#### COMPLIANCE

- ✓ Dobb-Frank ([DRC conflict free](#))
- ✓ REACH ([compliant](#))
- ✓ RoHS ([compliant](#))

### Wire Sizes Availability

Cat No.	Std. Wire Gauge	Diameter		Packaging	Sizes
4912	25	0.51 mm	0.020 in	Spool	½ lb
4900	21	0.81 mm	0.032 in	Pocket Pack	0.6 oz
4900	21	0.81 mm	0.032 in	Spool	¼, ½, or 1 lb
4915	19	1.02 mm	0.040 in	Spool	¼ or 1 lb
4916	18	1.27 mm	0.050 in	Spool	¼ or 1 lb
4917	16	1.57 mm	0.062 in	Spool	½ lb

### General Flux Parameters

Properties	Value
Residue Removal	Not required
Flux Percentage	2.2%
Flux Feature	Wets and spreads like a RA type flux and virtually non-splattering.
Shelf Life	5 y

### Flux Core Properties

The synthetically refined resin wets and spreads like a RA flux. This no clean flux is virtually non-spattering. It gives rise to a hard, non-conductive, and non-corrosive residue.

<b>Physical Properties</b>	<b>Method</b>	<b>Value</b>
Flux Classification	J-STD-004B EN29454-1	RELO Type 1.1.3
Flux Type	—	Resin
Flux Activity	—	Low
Halides %(wt)	—	<0.05%
Solid Flux Color	Visual	Lightly opaque
Softening Point of Flux Extract	—	24 °C [75 °F]
Acid Number (mgKOH/g sample)	IPC-TM-650 2.3.13	190–210
Copper Mirror	IPC-TM-650 2.3.32	No removal
Silver Chromate—Chlorides + Bromides	IPC-TM-650 2.3.33	Pass
Solder Spread	IPC-TM-650 2.4.46	130 mm <sup>2</sup>
Flux Residue Dryness	IPC-TM-650 2.4.47	Pass
Spitting of Flux-Cored Wire Solder	IPC-TM-650 2.4.48	0.30%
Corrosion Test	IPC-TM-650 2.6.15	Non-corrosive
Surface Insulation Resistance (SIR)	IPC-TM-650 2.6.3.3	2.3 × 10 <sup>11</sup> Ω
Bellcore (Telecordia)	Bellcore GR-78-CORE 13.1.3	6.1 × 10 <sup>11</sup> Ω
Electromigration	Bellcore GR-78-CORE 13.1.4	Pass
Post Reflow Residue	TGA Analysis	55%
Cleaning Requirements	—	Optional

### SAC305 Alloy Typical Literature Properties

<b>Physical Properties</b>	<b>Value</b> <sup>a)</sup>
Color	Silvery-white metal
Density @26 °C [78 °F]	7.49 g/cm <sup>3</sup>
Tensile Strength	29.7 N/mm <sup>2</sup> [4 310 lb/in <sup>2</sup> ]
Tensile Yield	25.7 N/mm <sup>2</sup> [3 720 lb/in <sup>2</sup> ]
Elongation	27%
Shear Strength @20 °C and 0.1 mm/min	27 N/mm <sup>2</sup> [3 900 lb/in <sup>2</sup> ]
@100 °C and 0.1 mm/min	17 N/mm <sup>2</sup> [2 500 lb/in <sup>2</sup> ]
Creep Strength @20 °C and 0.1 mm/min	13 N/mm <sup>2</sup> [1 900 lb/in <sup>2</sup> ]
@100 °C and 0.1 mm/min	5.0 N/mm <sup>2</sup> [730 lb/in <sup>2</sup> ]
Hardness	15 HB
<b>Electrical Properties</b>	<b>Value</b>
Volume Resistivity	13 μΩ·cm
Electrical Conductivity <sup>b)</sup>	16.6% IACS

Continued on the next page

Continued...

<b>Thermal Properties</b>	<b>Value</b>
Melting Point, Solidus	217 °C [423 °F]
Melting Point, Liquidus	221 °C [430 °F]
Tip Temperature Upper Limit	Do not exceed 350 °C [662 °F]
Coefficient of Thermal Expansion (CTE) <sup>c)</sup>	23.5 ppm/°C
Thermal Conductivity	58.7 W/(m·K)


**NOTE:** This table present typical literature values for SAC305 alloys.

a) N/mm<sup>2</sup> = mPa; lb/in<sup>2</sup> = psi;

b) International Annealed Copper Standard: 100% give  $5.8 \times 10^7$  S/m.

c) CTE unit conversions: ppm/°C =  $\mu\text{m}/(\text{m}\cdot\text{K}) = \text{in}/\text{in}/^\circ\text{C} \times 10^{-6} = \text{unit}/\text{unit}/^\circ\text{C} \times 10^{-6}$

### Solder Alloy Composition

<b>Properties</b>	<b>Value</b>	<b>Properties</b>	<b>J-STD-006C</b>	<b>4900–4917</b>
<i>MAIN INGREDIENTS</i>		<i>IMPURITIES</i> <sup>a)</sup>	<i>REQUIREMENTS</i>	<i>SPECIFICATIONS</i>
Sn	96.2 to 96.8%	Sb	≤0.20% Max	≤0.05% Max
Ag	2.8 to 3.2%	Bi	≤0.10% Max	≤0.05% Max
Cu	0.4 to 0.6%	In	≤0.10% Max	≤0.05% Max
		Pb	≤0.07% Max	≤0.05% Max
		Au	≤0.05% Max	≤0.002% Max
		As	≤0.03% Max	≤0.01% Max
		Fe	≤0.02% Max	≤0.01% Max
		Ni	≤0.01% Max	≤0.005% Max
		Al	≤0.005% Max	≤0.001% Max
		Zn	≤0.003% Max	≤0.001% Max
		Cd	≤0.002% Max	≤0.001% Max

a) Exceeds the requirements of J-STD-006C and meets ASTM B 32.

### Storage

Protect from direct heat or sunlight. Store between 18 to 27 °C [65 to 80 °F].

### Cleaning

The flux residue does not need to be removed for typical applications. If removal is desired, a solvent system like the *MG 4140* can be used. For best results, warm the cleaning solution to about 40 °C [104 °F].

### Health and Safety


Please see the 4900-4917 **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

**Health and Safety:** Avoid breathing fumes. Wash hands thoroughly after use. Do not ingest.

#### HMIS® RATING

<b>HEALTH:</b>	<b>* 1</b>
<b>FLAMMABILITY:</b>	<b>0</b>
<b>PHYSICAL HAZARD:</b>	<b>0</b>
<b>PERSONAL PROTECTION:</b>	

#### NFPA® 704 CODES



*Approximate HMIS and NFPA Risk Ratings Legend:*

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

### Packaging and Supporting Products

<i>Cat. No.</i>	<i>Form</i>	<i>Packaging</i>	<i>Net Weight</i>	
<b>4900-35G</b>	Solid wire	Pocket Pack <sup>a)</sup>	17 g	0.6 oz
<b>4900-112G</b>	Solid wire	Spool	113 g	0.25 lb
<b>4900-227G</b>	Solid wire	Spool	227 g	0.5 lb
<b>4900-454G</b>	Solid wire	Spool	454 g	1.0 lb
<b>4900-18GX2</b>	Solid wire	Pocket Pack <sup>b)</sup>	21 g	0.7 oz
<b>4912-227G</b>	Solid wire	Spool	227 g	0.5 lb
<b>4915-112G</b>	Solid wire	Spool	113 g	0.25 lb
<b>4915-454G</b>	Solid wire	Spool	454 g	1.0 lb
<b>4916-112G</b>	Solid wire	Spool	113 g	0.25 lb
<b>4916-454G</b>	Solid wire	Spool	454 g	1.0 lb
<b>4917-227G</b>	Solid wire	Spool	227 g	0.5 lb

a) Box of 25 pocket packs

b) Case pack of 2



# SAC305 No Clean Solder Wire 4900–4917 Technical Data Sheet

ISO 9001:2008 Registered Quality System. Burlington, Ontario, CANADA SAI Global File: 004008

4900–4917

## Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at [www.mgchemicals.com](http://www.mgchemicals.com).

Email: [support@mgchemicals.com](mailto:support@mgchemicals.com)

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

+ (44) 1663 362888 (UK & Europe)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**  
1210 Corporate Drive  
Burlington, Ontario, Canada  
L7L 5R6

**Head Office**  
9347–193rd Street  
Surrey, British Columbia, Canada  
V4N 4E7

## Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.